


Specifications

20-02

ISO 10581 Heterogeneous PVC		mFLOR 20-02
ISO 24340	Thickness of the wear layer	0.20 mm + Polyurethane
ISO 24346:2006	Overall thickness	2.0 mm
ISO 23997:2008	Weight	+/- 3.550 kg/m ²
ISO 23999:2008	Dimensional stability (average value)	✓
	In longitudinal direction (%):	-0.05
	In cross direction (%):	-0.05
ISO 24344:2008, method A	Flexibility	20 mm
ISO 24343-1:2012	Residual indentation	-0.08 mm
ISO 4918:2016	Castor chair test	✓
ISO 105-B02:2013	Colour fastness to artificial light	6-8, depending on design
ISO 10582:2017	Usage category	22+ - General domestic use
EN 1081:1998	Electrical resistance	
	Method A, vertical resistance	6.6x10 ¹² Ω
	Method C, horizontal resistance	1.5x10 ⁷ Ω
EN 1815:2016, method A	Static electrical propensity (anti-static)	Rubber sole: 0.5 kV
EN 13893:2002	Slip resistance (μ)	0.4
ISO 8302:1991 EN 12667:2001	Thermal resistance (thermal conductivity)	0.007 m ² K/W
ISO 26987:2008	Staining and resistance to chemicals	Class O, Good
EN ISO 10140-1 - 5:2010	Impact sound insulation	ΔL _w 1 dB
EN ISO 354:2003	Sound absorption	α _w 0.05
EN 13501-1:2007 + A1:2009	Classification of burning behaviour	Bfl - s1
EN 71	Toxicity	Non toxic
Low VOC certified		✓
	Underfloor heating	28°C



www.mflor.com.au

mFLOR®